

Report # K-418805-1505F01-R00

## Test Report

Kinectrics Inc., 800 Kipling Avenue, Unit 2  
Toronto, Ontario, Canada  
Tel: 416-207-6000, www.kinectrics.com



Samples Received:  
Apr-28-15

Samples Tested:  
May-12-15

### Tested for

ArcWear.com  
Hugh Hoagland  
ArcTesting@ArcWear.com  
502-333-0510

### Contact information for item tested:

BSD GmbH  
Lutherstrasse 33  
Grossroehrsdorf 01900 Germany  
+49 35952 41025

### Test item description

BSD GmbH, Faceshield,  
Style BSD ErgoS 2 plus; Article No. 7406311,  
Lens: BSD 50 Polycarbonat Lens, Polycarbonate, Grey, Thickness 1.5 mm,  
Hard Hat: Voss, Elektriikerhelm,  
ArcWear# 1505F01

### Reference Standard

ASTM F2178-12  
Standard Test Method for Determining the Arc Rating and Standard Specification for Eye or Face Protective Products

### Test Parameters:

Test current: 8 kA	Number of samples analysed: 20
Arc Gap: 305 mm	
Distance to Fabric: 305 mm	Incident Energy Range: 10 to 16 cal/cm <sup>2</sup>

**Arc Rating, ATPV = 12 Cal/cm<sup>2</sup>**  
**Heat Attenuation Factor, HAF = 88%**

No variations to standard method noted.  
Break-open Ebt not achieved or determined.  
Samples tested as received, pre-test laundering as required by standard was arranged by client.

### Summary

The Arc Rating of this material is intended for use as part of a flame resistant garment or system for workers exposed to electric arcs. The test result is applicable only to the test item as described; other fiber blends, weaves, finishing or dye may have different protection level. The test articles are tested as received; no test is done to validate the fiber content or composition. The Arc Rating was calculated based on the data obtained and analysed in accordance with the latest version of the applicable standards. The individual test sheets, graphs, photographs of the samples and video of every test are provided in digital format to the Client for review.

The arc testing performed to the above mentioned Standard is accredited by the Standards Council of Canada (SCC) to conform to the requirements of CAN-P-4E (ISO/IEC 17025:2005). Accreditation by the Standards Council of Canada (SCC) is a mark of competence and reliability recognized throughout the world.

Kinectrics Inc takes reasonable steps to ensure that all work performed shall meet the industry standards as set out in Kinectrics Inc.'s Quality Manual, and that all reports shall be reasonably free of errors, inaccuracies or omissions. KINETRICS INC. DOES NOT MAKE ANY WARRANTY OR REPRESENTATION WHATSOEVER, EXPRESS OR IMPLIED, WITH RESPECT TO THE MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE OF ANY INFORMATION CONTAINED IN THIS REPORT OR THE RESPECTIVE WORKS OR SERVICES SUPPLIED OR PERFORMED BY KINETRICS INC. Kinectrics Inc. does not accept any liability for any damages, either directly, consequentially or otherwise resulting from the use of this report.

Note: The test performed does not apply to electrical contact or electrical shock hazard.

©Kinectrics. Partial reproduction of this report is strictly prohibited without the express written consent of Kinectrics Inc.

Prepared by:

Approved by:

Andrew Haines  
HCL Technologist  
Ph: 416-207-6000

Claude Maurice  
Test laboratory manager  
Kinectrics Inc.

Note: For verification about results in this report, please forward copy of the report or inquiry to [hcl@kinectrics.com](mailto:hcl@kinectrics.com)